


# TECHNICAL DATA SHEET

<b>Name :</b>	<b>Nylon 70D/190T WR PVC REACH</b>		
<b>Supplier :</b>	KINETIC s.r.o. SNP 9/6 ; 796 07 Držovice IČO:27728234 ; DIČ: CZ27728234 tel.: 582 365 770 email : kinetic@kinetic.cz		
<b>Manufactured :</b>	Taiwan		
<b>Description :</b>	Nylon 70D/190T WR PVC REACH		
<b>Textile :</b>	<b><u>100% NYLON</u></b>		
<b>Lamination :</b>	PVC		
<b>Weight :</b>	189 g/m2		+/- 5%
<b>Dimensions :</b>	fabric width 58" - length 1 roll 50m		
<b>Tensile strength :</b>	warp	1902	+/- 5%
<b>(ISO 13934-1 (N))</b>	weft	268	+/- 5%
<b>Tear strength :</b>	warp	71	+/- 5%
<b>(ISO13937-2 (N))</b>	weft	44	+/- 5%
<b>Adhesion of coating to fabric</b>	warp	30.83	+/- 5%
<b>ASTM D751-19 (N)</b>	weft	28.84	+/- 5%
<b>Water column:</b>			
<b>AATCC-127 (mmH2O)</b>		>2000	
<b>Abrasive resistance</b>			
<b>ISO 12947-2 (Cycles)</b>		25000	
<b>Laundry symbols :</b>	 <p style="text-align: center;">DO NOT WASH, DO NOT BLEACH, DO NOT TUMBLE DRY, DO NOT IRON, DO NOT DRY CLEAN</p>		
<b>Suitable method of treatment :</b>	Textile side of the fabric clean either dry with a soft brush or slightly wet cloth.  The fabric should be left to dry at room temperature.		

In Drzovice 16.7.2024

**KINETIC s.r.o.**

SNP 9/6 • 796 07 Držovice

tel.: +420 582 365 770-2

fax: +420 582 365 769

č.ú.. 377 886 323 / 0300

IČ: 277 28 234 • DIČ: CZ27728234



Ing. Hlahůlek Ivo

Jednatel společnosti Kinetic s.r.o.

<https://cdn.discordapp.com/attachments/550828469030879243/792595979432886302/eof6mfhyjl761.jpg>