




+420 582 365 770  
kinetic@kinetic.cz  
SNP 9/6, 796 07 Držovice



## TECHNICAL DATA SHEET

<b>Name :</b>	<b>PES 500D/64T PVC WR UV</b>		
<b>Supplier :</b>	KINETIC s.r.o. SNP 9/6 ; 796 07Držovice IČO:27728234 ; DIČ: CZ27728234 tel.: 582 365 770 email : kinetic@kinetic.cz		
<b>Manufactured :</b>	Taiwan		
<b>PROJECT</b>	TESTING RESULTS	TESTING STANDART	TOLERANCE
<b>Description</b>	PES 500D/64T PVC WR UV		
<b>Textile :</b>	<u>100% polyester</u>		
<b>Lamination :</b>	PVC		
<b>Dyeing method:</b>	Sollution dyeing		
<b>Weight :</b>	442,27	ISO 3801 (g/m2)	+/- 5%
<b>Dimensions :</b>	fabric width 58" - length 1 roll 50m		+/- 5%
<b>Tensile strength:</b>			
<b>warp</b>	1432.73	ISO 13934-1 (N)	+/- 5%
<b>weft</b>	1313.65	ISO 13937-2 (N)	+/- 5%
<b>Tear strength:</b>			
<b>warp</b>	86.32	ISO 13937-2 (N)	+/- 5%
<b>weft</b>	71.75		+/- 5%
<b>Abrasion resistance :</b>	50 000	ATCC-127 (cycles)	+/- 5%
<b>Water column :</b>	2498	ATCC-127 (mmH2O)	+/- 5%
<b>Others</b>			
<b>Laundry symbols :</b>	 DO NOT WASH    DO NOT BLEACH    DO NOT TUMBLE DRY    DO NOT IRON    DO NOT DRY CLEAN		
<b>Suitable method of treatment :</b>	Textile side of the fabric clean either dry with a soft brush or slightly wet cloth The fabric should be left to dry at room temperature		
<b>Recommended</b>	Recommended to store in a horizontal position, in a dry and well-ventilated area, away from		
In Drzovice 1.10.2024			