



+420 582 365 770
 kinetic@kinetic.cz
 SNP 9/6, 796 07 Držovice



TECHNICAL DATA SHEET

| | | | |
|---------------------------------------|---|-------------------------|------------------|
| Name : | POLYESTER 600D/84T WR PU UV | | |
| Supplier : | KINETIC s.r.o. SNP 9/6 ; 796 07Držovice IČO:27728234 ; DIČ: CZ27728234 tel.: 582 365 770 email : kinetic@kinetic.cz | | |
| Manufactured : | Taiwan | | |
| PROJECT | TESTING RESULTS | TESTING STANDART | TOLERANCE |
| Description | POLYESTER 600D/84T WR PU UV | | |
| Textile : | <u>100% polyester</u> | | |
| Lamination : | Polyuretan | | |
| Dyeing method: | Sollution dyeing | | |
| Weight : | 266,73 | ISO 3801 (g/m2) | +/- 5% |
| Dimensions : | fabric width 58" - length 1 roll 50m | | +/- 5% |
| Tensile strength: | | | |
| warp | 2084.60 | ISO 13934-1 (N) | +/- 5% |
| weft | 1406.99 | ISO 13937-2 (N) | +/- 5% |
| Tear strength: | | | |
| warp | 103.79 | ISO 13937-2 (N) | +/- 5% |
| weft | 75.50 | | +/- 5% |
| Abrasion resistance : | 250 000 | ATCC-127 (cycles) | +/- 5% |
| Water column : | 694 | ATCC-127 (mmH2O) | +/- 5% |
| Others | | | |
| Laundry symbols : | DO NOT WASH DO NOT BLEACH DO NOT TUMBLE DRY DO NOT IRON DO NOT DRY CLEAN | | |
| Suitable method of treatment : | Textile side of the fabric clean either dry with a soft brush or slightly wet cloth The fabric should be left to dry at room temperature | | |
| Recommended | Recommended to store in a horizontal position, in a dry and well-ventilated area, away from | | |
| In Drzovice 1.10.2024 | | | |